

# Data Sheet

# L'HERMETIC

# **FUNCTIONALITY**

## Sealant made of natural rubbers, synthetic resins and graphite in alcohol solution

- For sealing engine and housing joints, all mechanical parts, flat seals, pipes, threaded joints, valves, flanges, tanks, cisterns, retention trays, etc.
- No corrosive effect on rubber and metal.
- Can be removed when hot

# **Technical characteristics**

Specifications	Characteristics
Appearance	Black, fluid paste
Viscosity	2,800 mPa.s
Solids content	76%
Density	1.18
Temperature stability	120 ℃ (140 ℃ peak)
Water solubility	Insoluble in cold and hot water and steam
Chemical resistance	Mineral oils, diesel fuel, fuel oil, petroleum, kerosene, superfuel 95 and 98 (cold, hot and pressurised)

### <u>Use</u>

#### Preparation

The surfaces must be clean, dry and degreased.

#### Directions for use

- Mix the product well before use
- Spread the product using a brush
- For metal on metal joints, apply a thin layer of the product to both parts to be assembled
- For use with a seal (paper, metalloplastic), insert the seal between the 2 surfaces coated with product
- Wait a few minutes before assembling
- Clamp the parts

#### Material cleaning

Ethyl alcohol

## <u>Tip</u>

If the product thickens, dilute it with 5% ethyl alcohol if required

# Storage



GEB SAS - BP 62062 - Tremblay en France 95972 Roissy Charles de Gaulle Cédex - France Tel. +33 (0)1 48 17 99 99 - Fax +33 (0)1 48 17 98 00 SIREN No.: 500 674 056



p: 1 of 1

Store between +5  $^{\circ}$ C and +30  $^{\circ}$ C. At +20  $^{\circ}$ C, the shelf life of the product in its original, sealed packaging is 18 months.

The Safety Data Sheet is available online at <u>www.quickfds.com</u>. The information provided in this data sheet is given in good faith and is the result of measurements done in our laboratory. Given the number of materials, the quality differences and the diversity of working methods, we recommend that users carry out preliminary testing under actual conditions of use. This document may be modified without warning in line with changes to the products or according to our knowledge. We therefore recommend that you check that you have the latest version before using the product.



GEB SAS - BP 62062 - Tremblay en France 95972 Roissy Charles de Gaulle Cédex - France Tel. +33 (0)1 48 17 99 99 - Fax +33 (0)1 48 17 98 00 SIREN No.: 500 674 056



p: 2 of 2