

BLACKFIRE

FUNCTIONALITY

Quick-drying, solvent-based, acrylic paint for decoration, marking, finishing and touching up

- Can be applied to all surfaces (carry out a test on plastic first): Fireguards and chimney plates, exhaust pipes, engines, stoves, ovens, radiators, etc.
- Can be applied to metals: aluminium, iron, steel, etc. / Wood: plywood, chipboard, etc. / Cement / Stone
- Fully resistant to thermal shocks
- Anti-corrosion properties

Technical characteristics

Specifications	Characteristics
Paint appearance	Black liquid
Odour	Solvent-based:
Appearance of the dry film	Matt black
Temperature stability	400 °C
Drying time (dust-free) at 20 °C	15 min
Total drying time	1 hour
Coverage	3 to 4 m ²

Use

Preparation

- For best results, use the paint between 15 °C and 25 °C
- Degrease the surfaces to be treated with acetone and remove traces of rust using a wire brush or an abrasive
- Shake the spray can upside down vigorously for 1 minute until the ball can be heard rattling

Directions for use

- Spray the right way up approximately 25-30 cm from the surface to be created, cross-coating and without stopping to prevent runs
- Leave to dry for 15 to 20 minutes before applying a 2nd coat
- Leave to dry for at least 1 hour before subjecting to high temperatures
- Bleed the can upside down to prevent nozzle blockages

Consumption

- 1 spray can covers 3 to 4 m²

Material cleaning

The Safety Data Sheet is available online at www.quickfds.com. The information provided in this data sheet is given in good faith and is the result of measurements done in our laboratory. Given the number of materials, the quality differences and the diversity of working methods, we recommend that users carry out preliminary testing under actual conditions of use.

This document may be modified without warning in line with changes to the products or according to our knowledge. We therefore recommend that you check that you have the latest version before using the product.

- Acetone or white spirit

Storage

Keep away from frost and direct sunlight.

Store between +5 °C and +40 °C.

At 20 °C, the shelf life of the product in its original, sealed packaging is 2 years.

Comments

Do not scrape the paint while the sheet metal is still very hot as this would damage the coating. Its mechanical strength will return after cooling.

BLACKFIRE will be stronger once it has been exposed to heat.

Fresh runs can be removed with acetone or white spirit.

The Safety Data Sheet is available online at www.quickfds.com. The information provided in this data sheet is given in good faith and is the result of measurements done in our laboratory. Given the number of materials, the quality differences and the diversity of working methods, we recommend that users carry out preliminary testing under actual conditions of use.

This document may be modified without warning in line with changes to the products or according to our knowledge. We therefore recommend that you check that you have the latest version before using the product.



GEB SAS – BP 62062 – Tremblay en France
95972 Roissy Charles de Gaulle Cédex - France
Tel. +33 (0)1 48 17 99 99 - Fax +33 (0)1 48 17 98 00
SIREN No.: 500 674 056

www.geb.fr

p: 2 of 2