

## ALUXIL

### FUNCTIONALITY

**Shiny paint with aluminium particle and binder base resistant to very high temperatures.**

- Heating installations: pipes, smoke boxes, boiler parts, metal flues, etc.
- Industry: pipes for high-temperature fluids or steam, industrial boiler rooms.
- Automotive/Yachting: exhaust manifolds and mufflers.

### Technical characteristics

Specifications	Characteristics
Appearance of the dry film	Shiny aluminium
Temperature stability	+600 °C
Drying time (dust-free)	20 min at +20 °C
Total drying time	1 hour
Coverage	Approximately 3 to 4 m <sup>2</sup> in 2 coats for 650 ml
Mechanical strength, thermal resistance, chemical resistance	Very good resistance to scratches, thermal shocks and chemical agents (hydrocarbons)

### Use

#### **Preparation**

- Remove any traces of rust from the surface to be painted using a wire brush or an abrasive.
- Degrease and remove dust if necessary.

#### **Directions for use**

- Shake the spray can until the steel ball can be heard rattling, then continue for 1 minute. Spray evenly holding the can 30 cm from the surface to be painted and by cross-coating.
- **ALUXIL** will be dust-free in approximately 15 minutes.
- Leave to dry for 1 hour before subjecting the painted substrate to high temperatures.
- Bleed the can upside down after use to prevent nozzle blockages.

#### **Consumption**

- Approximately 3 to 4 m<sup>2</sup> in 2 coats for 650 ml

#### **Material cleaning**

- White spirit for fresh drips

### Tip

Bleed the can upside down after use to prevent nozzle blockages.

## Storage

Store between -5 °C and +40 °C.

At +20 °C, the shelf life of the product in its original, sealed packaging is 3 years.

The Safety Data Sheet is available online at [www.quickfds.com](http://www.quickfds.com). The information provided in this data sheet is given in good faith and is the result of measurements done in our laboratory. Given the number of materials, the quality differences and the diversity of working methods, we recommend that users carry out preliminary testing under actual conditions of use.

This document may be modified without warning in line with changes to the products or according to our knowledge. We therefore recommend that you check that you have the latest version before using the product.



GEB SAS – BP 62062 – Tremblay en France  
95972 Roissy Charles de Gaulle Cédex - France  
Tel. +33 (0)1 48 17 99 99 - Fax +33 (0)1 48 17 98 00  
SIREN No.: 500 674 056

**[www.geb.fr](http://www.geb.fr)**

p: 2 of 2